

## WAX SOLUTION 9872

### DESCRIPTION

WAX SOLUTION 9872 (5 % solution).

Recommended dosage in gelcoat to obtain topcoat quality: 3 %.

### TYPICAL PROPERTIES

Paraffin wax 5 % solution dissolved in styrene.

Properties	Unit	Value	Test method
Density	g/cm <sup>3</sup>	0.89-0.92	ISO 2811-2001
Flash point	°C	32	ASTM D 3278-95
Storage stability from date of manufacture	months	12	G180

Wax may crystallize at lower temperatures hence the solution should be kept at room temperature before use.

The information herein is general information designed to assist customers in determining whether our products are suitable for their applications. Our products are intended for sale to industrial and commercial customers. We require customers to inspect and test our products before use and to satisfy themselves as to contents and suitability for their specific applications. We warrant that our products will meet our written specifications. **Nothing herein shall constitute any other warranty express or implied, including any warranty of merchantability or fitness for a particular purpose**, nor is any protection from any law or patent to be inferred. All patent rights are reserved. The exclusive remedy for all proven claims is limited to replacement of our materials and in no event shall we be liable for special, incidental or consequential damages.